

PRODUCT DATASHEET

LEXAN™ 9034 SHEET

DESCRIPTION

LEXAN™ 9034 uncoated polycarbonate sheet is the standard grade of LEXAN sheet for transparent protective glazing. High-impact LEXAN 9034 sheet may be an excellent candidate for primary glazing, or on either side of existing glazing for economical protection against breakage or intrusion. A better insulator than glass, LEXAN 9034 sheet may contribute to lower energy costs.

TYPICAL PROPERTY VALUES

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	—	1.20
Refractive Index @ 77°F	ASTM D542A	—	1.586
Light Transmission (Average), 1/8" disk	ASTM D1003	%	88
Rockwell Hardness	ASTM D785	—	M70
Abrasion Resistance, Taber Abrader, CS-17 wheel	ASTM D1044	mg/1,000 cycles	10
Water Absorption, Equilibrium, 24 hrs	ASTM D570	%	0.15
@ 73°F			0.35
@ 212°F			0.58
Mechanical			
Tensile Strength @ Yield	ASTM D638	psi	9,000
@ Ultimate			9,500
Tensile Modulus	ASTM D638	psi	345,000
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	345,000
Flexural Endurance @ 1,800 cycles/min,			
73°F, 50% RH	ASTM D671	psi	1,000
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTM D695	psi	345,000
Elongation	ASTM D638	%	110
Poisson's Ratio	—	—	0.37
Izod Impact Strength Notched @ 1/8"	ASTM D256A	ft-lbs/in	12–16
Unnotched @ 1/8"			60 (no failure)
Tensile Impact Strength, S-Type Specimen	ASTM 1822	ft-lbs/in ²	225–300
Shear Strength @ Yield	ASTM D732	psi	6,000
@ Ultimate			10,000
Shear Modulus	ASTM D732	psi	114,000
Deformation Under Load @ 4,000 psi @ 73°F	ASTM D621	%	0.2
@ 158°F			0.3
Thermal			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 ⁻⁵
Coefficient of Thermal Conductivity	ASTM C177	Btu•in/hr•ft ² •°F	1.35
Specific Heat @ 40°C		cal/gm/°C	0.30
Heat Deflection Temperature @ 264 psi	ASTM D648	°F	270
@ 66 psi			280
Brittle Temperature	ASTM D746	°F	-211
Relative Thermal Index, Electrical properties	UL746B	°C	130
Relative Thermal Index, Mechanical properties with impact	UL746B	°C	125
Relative Thermal Index, Mechanical properties without impact	UL746B	°C	125
Flammability			
Horizontal Burn (Flame Spread) AEB	ASTM D635	in	<1

PRODUCT DATASHEET

LEXAN™ 9034 SHEET

Property	Test Method	Units	Value
Electrical			
Dielectric Constant @ 10 Hz	ASTM D150	—	2.96
@ 60 Hz			3.17
Volume Resistivity	ASTM D257	ohm-cm	8.2×10^{16}
Power Factor @ 60 Hz	ASTM D150		0.0009
@ 1,000,000 Hz			0.010
Arc Resistance	ASTM D495	sec	
Stainless Steel Strip Electrodes			10–11
Tungsten Electrodes			120

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics representative or SABIC Innovative Plastics Quality Services Department.

™ Trademarks of SABIC.

CODE COMPLIANCE

Underwriters Laboratories

LEXAN 903x Sheet is listed as a Burglary-Resisting Glazing Material according to UL Standard 972.

UL File Number: E121562

Americas Headquarters

SABIC Innovative Plastics
One Plastics Avenue
Pittsfield, MA 01201
USA
T +1-413-448-7125
Toll-free: 1-800-323-3783
F +1 (888) 443-2033
sfsustomerservice@sabic-ip.com

European Headquarters

SABIC Innovative Plastics
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 293684
F +31 164 293272
Sfs.info@sabic-ip.com

Pacific Headquarters

SABIC Innovative Plastics
Specialty Film & Sheet
1266 Nanjing Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
T +86 21 62881088 ext. 6733
F +86 21 6288 0818

E-mail

sfsustomerservice@sabic-ip.com



* Trademark of SABIC Innovative Plastics IP BV

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

™ Trademark of SABIC.

sabic-ip.com/sfs